

Rapid Set Epoxy Paste Adhesive



Technical Data Sheet

DESCRIPTION	<p>Megapoxy PF is a rapid set epoxy adhesive which sets in seven minutes and attains more than half its ultimate strength within 15 minutes of mixing.</p> <p>Megapoxy PF “hardens-as-you-hold-it” for immediate on the spot emergency repairs to tanks, pipes, machinery, concrete structures etc.</p> <p>Properly mixed Megapoxy PF will not stain or discolour white or light coloured marble and ceramics</p>																					
RECOMMENDED APPLICATIONS	Bonding <ul style="list-style-type: none"> • Precast concrete articles • Metal to metal or concrete • Grouting bolts • Natural stones • Bricks and ceramics • Bonding compressed cement sheet 	Filling and Repair <ul style="list-style-type: none"> • Concrete pipes and tanks Fibreglass articles • Fibreglass articles • Concrete floors and stairs • Concrete column • Insitu formed concrete • Flush-filling countersunk screws in fibre cement sheet 																				
PROPERTIES	<table border="1"> <tr> <td>Mixing Ratio by Volume</td> <td>1 Part A to 1 Part B</td> </tr> <tr> <td>Work Time at 25°C:</td> <td>3 minutes</td> </tr> <tr> <td>Minimum Cure Time at 15°C</td> <td>2 hours</td> </tr> <tr> <td>Minimum Cure Time at 25°C</td> <td>1 hours</td> </tr> <tr> <td>Minimum Cure Time at 35°</td> <td>30 minutes</td> </tr> <tr> <td>Minimum Application Temperature</td> <td>10°C</td> </tr> <tr> <td>Maximum Operating Temperature</td> <td>80°C</td> </tr> <tr> <td>Colour Part A</td> <td>White</td> </tr> <tr> <td>Colour Part B</td> <td>White or Dark Grey</td> </tr> <tr> <td>Appearance Mixed</td> <td>White or Grey</td> </tr> </table>		Mixing Ratio by Volume	1 Part A to 1 Part B	Work Time at 25°C:	3 minutes	Minimum Cure Time at 15°C	2 hours	Minimum Cure Time at 25°C	1 hours	Minimum Cure Time at 35°	30 minutes	Minimum Application Temperature	10°C	Maximum Operating Temperature	80°C	Colour Part A	White	Colour Part B	White or Dark Grey	Appearance Mixed	White or Grey
Mixing Ratio by Volume	1 Part A to 1 Part B																					
Work Time at 25°C:	3 minutes																					
Minimum Cure Time at 15°C	2 hours																					
Minimum Cure Time at 25°C	1 hours																					
Minimum Cure Time at 35°	30 minutes																					
Minimum Application Temperature	10°C																					
Maximum Operating Temperature	80°C																					
Colour Part A	White																					
Colour Part B	White or Dark Grey																					
Appearance Mixed	White or Grey																					
CURED PROPERTIES	<table border="1"> <tr> <td>Compressive Strength - ASTM D695-23</td> <td>70Mpa</td> </tr> <tr> <td>Bond Strength Concrete - ASTM D4541</td> <td>>3Mpa</td> </tr> <tr> <td>Tensile Bond Strength Steel - ASTM D897-08</td> <td>10Mpa</td> </tr> <tr> <td>Modulus of Elasticity - ASTM D695</td> <td>2Gpa</td> </tr> <tr> <td>Flexural Strength ASTM D790-17</td> <td>46Mpa</td> </tr> <tr> <td>Tensile Strength - ASTM D638-22</td> <td>21Mpa</td> </tr> <tr> <td>Tensile Shear Strength - ASTM D1002-10</td> <td>8Mpa</td> </tr> <tr> <td>Hardness - Shore D - ASTM D2240-00</td> <td>75</td> </tr> <tr> <td>Coefficient of Linear Thermal Expansion, Mean</td> <td>57.9 x 10⁻⁶ (mm/mm/°C)</td> </tr> <tr> <td>Dielectric Strength 50Hz @25°C(Kv/cm)</td> <td>190</td> </tr> </table>		Compressive Strength - ASTM D695-23	70Mpa	Bond Strength Concrete - ASTM D4541	>3Mpa	Tensile Bond Strength Steel - ASTM D897-08	10Mpa	Modulus of Elasticity - ASTM D695	2Gpa	Flexural Strength ASTM D790-17	46Mpa	Tensile Strength - ASTM D638-22	21Mpa	Tensile Shear Strength - ASTM D1002-10	8Mpa	Hardness - Shore D - ASTM D2240-00	75	Coefficient of Linear Thermal Expansion, Mean	57.9 x 10 ⁻⁶ (mm/mm/°C)	Dielectric Strength 50Hz @25°C(Kv/cm)	190
Compressive Strength - ASTM D695-23	70Mpa																					
Bond Strength Concrete - ASTM D4541	>3Mpa																					
Tensile Bond Strength Steel - ASTM D897-08	10Mpa																					
Modulus of Elasticity - ASTM D695	2Gpa																					
Flexural Strength ASTM D790-17	46Mpa																					
Tensile Strength - ASTM D638-22	21Mpa																					
Tensile Shear Strength - ASTM D1002-10	8Mpa																					
Hardness - Shore D - ASTM D2240-00	75																					
Coefficient of Linear Thermal Expansion, Mean	57.9 x 10 ⁻⁶ (mm/mm/°C)																					
Dielectric Strength 50Hz @25°C(Kv/cm)	190																					

Technical Data Sheet

CHARACTERISTICS	<ul style="list-style-type: none"> • VOC Free • Smooth and easily workable • Simple 1:1 mix ratio • Creamy texture, blends easily • Non sag on vertical surfaces or overhead surface • Sets in 3 minutes at 25°C - 90% cure within 1 hour at 25°C • Very high strength permanent bonds • Excellent tensile and compressive strengths, superior to concrete • Excellent chemical resistance • Can be machined after 30 minutes cure at 25°C
SURFACE PREPARATION	<p>Concrete</p> <p>Concrete should be free from grease and oil. If necessary, clean with industrial heavy duty degreaser. When clean, remove surface laitance. This is best done by mechanical abrasion such as scabbling, grit blasting or grinding. If this is not possible acid etching must be carried out. Mix concentrated hydrochloric acid with equal volume of water and spread at the rate of 0.5 litre per square meter of concrete surface. Allow to react for about 10 minutes and wash the area thoroughly and scrub with a stiff bristled broom to remove loose sand. Allow to dry for 24 hours. For maximum adhesion the concrete should be surface dry.</p> <p>Metal Surfaces</p> <p>Metals should be grit blasted to AS CK 9.4 - 1964 Class 3 finish. If this is not possible, mechanically abrade the surface to a clean, bright metal surface. Once this abrasion is complete, degrease the surface by flooding with an industrial grade degreaser. Wire brushing is not entirely satisfactory and gives minimal adhesion only.</p> <p>Coated Surfaces</p> <p>It is recommend to remove all coatings prior to bonding, bonding to coated surfaces will give inferior bond strengths compared to bonding directly to a prepared substrate.</p> <p>Concrete:</p> <p>The surface may be either flame-cleaned, or mechanically treated with a scutching tool, to remove all traces of paint. Complete the preparation by diamond grinding or scabbling.</p> <p>Metals:</p> <p>Steps should be taken to remove all paint and/or galvanizing. Good quality paint stripper should be used, followed by grit blasting or grinding to a bright metal finish.</p>
IMPORTANT INFORMATION	<p>It is essential that the correct mixing ratio be used and that the Part A and Part B are thoroughly mixed together before use. Inaccuracies and poor mixing will result in lower physical properties of the cured system and, if the error is sufficiently large, the system may not cure satisfactorily and discolour on ageing.</p>
CLEANING	<p>To keep mixing implements and working tools clean, use Megapoxy Thinners. Use disposable rubber gloves to protect hands and maintain proper industrial hygiene. For further details refer to the Megapoxy PF Safety Data Sheet.</p>
PACKAGING	<p>Megapoxy PF is available in 4lt & 20 litre kits and in Grey or White. Product should be stored in cool dry store.</p>
TECHNICAL SERVICE	<p>All purchasers of Megapoxy Products, are encouraged to avail themselves of our Technical Service for our Megapoxy Products. The information in this Bulletin is correct at time of publication, however continual research and development is being carried out and specs may change without notice.</p>